



Genesis® M Single Stage System

GENESIS® M G2

ACRYLIC POLYURETHANE SYSTEM DESIGNED
FOR HIGH PRODUCTION MANUFACTURING

EASY APPLICATION

SAG RESISTANT

GOOD FLOW AND LEVELING

EXCELLENT GLOSS

FULL SOLID AND METALLIC COLOR PALETTE

AIR DRY OR BAKE

LOW HAPS AND LOW VOC (2.8 & 3.5 VOC)



SHERWIN-WILLIAMS
Automotive Finishes

The Sherwin-Williams Company
4440 Warrensville Center Road
Warrensville Heights, OH 44128
1-800-798-5872

www.sherwin-automotive.com

GENESIS[®] M G2

TECHNICAL DATA	TEST	RESULTS	REAL WORLD BENEFITS
APPEARANCE		EXCELLENT	
20° Gloss	ASTM D523	80+	Increases consumer satisfaction and sales potential
60° Gloss	ASTM D523	90+	
Distinctness Of Image (DOI)	ASTM D5767	90+	
ACT Orange Peel Rating		>5	
FLEXIBILITY		EXCELLENT	
Impact Resistance > 80 in./lb.	ASTM 2794	Pass	Resists chipping in extreme conditions
1/8" Mandrel Bend	ASTM D522	Pass	
Frozen Gravelometer Resistance	ASTM D3170	Pass	
CHEMICAL RESISTANCE		EXCELLENT	
Anti Freeze		No Effects	Resists appearance defects and protects substrates from attack following spills
Diesel Fuel		No Effects	
Gasoline		No Effects	
Motor Oil		No Effects	
Muriatic Acid (2:1 with water)		No Effects	
Solvent (Methyl Ethyl Ketone)		No Effects	
Acid (Sulfuric Acid)		No Effects	
Alkali (Sodium Hydroxide)		No Effects	
MOISTURE RESISTANCE		EXCELLENT	
Humidity Resistance	ASTM D2247	250 Hours No Effect	Resists appearance defects and assists protection of substrate in high moisture regions
CORROSION RESISTANCE		EXCELLENT	
Salt Spray	ASTM B117	1000 Hours No Effect	Resists appearance defects and assists protection of substrate in harsh environment
EXTERIOR WEATHERABILITY		EXCELLENT	
Xenon Accelerated Weathering	ASTM D6695	Pass Gloss and Color Retention	Resists appearance changes over time
5 Year 5° South Black Box Florida Weathering	ASTM D4141	Pass Gloss and Color Retention	

For more information on this product, contact 1-800-798-5872 or visit www.sherwin-automotive.com